

Additive designed to improve levelling and to increase scratch and abrasion resistance

Tesistance				
Composition:	Organically modified polysiloxane			
Data:	Active ingredients Solvent Density at 20 °C Refractive index Flashpoint Appearance	: : : :	50 - 53 % isobutanol 0.90 - 0.92 g/cm ³ 1.418 - 1.428 27 °C clear, colourless liquid	DIN 51757 DIN 53491 ISO 3679
Properties:	 EFKA-3030: improves levelling increases scratch and abrasion resistance prevents floating improves anti-blocking characteristics compared to dimethylpolysiloxane, EFKA-3030 is universally compatible with various coating systems and does not cause cratering even in excessively high concentrations 			
Application:	EFKA-3030 is used in water and solvent based industrial coatings, particularly for spray application.			
Addition:	0.1 - 0.3% on total formulation			
Incorporation:	EFKA-3030 can be added at any stage during the production process. When added during the dispersion process, it speeds up wetting.			
Storage:	EFKA-3030 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.			
Packaging:	25 kg and 180 kg non-returnable containers			