

F	low	age	nt

Composition: Solvent blend of high-boiling aromatics, ketones and esters, including a

highly compatible polysiloxane

**Data:** Density at 20 °C : 0.85 - 0.87 g/cm<sup>3</sup> DIN 51757

 Refractive index
 : 1.477 - 1.487
 DIN 53491

 Flashpoint
 : 42 °C
 ISO 3679

Appearance : clear, colourless liquid

**Application:** EFKA-3037:

 prevents surface defects like cratering, scarring or blistering in airdrying and stoving paints

shortens setting time

· prevents cob-webbing in stoving enamels

prevents streaking during painting and spraying of chlorinated rubber

and coatings based on other chlorinated polymers

· prevents chilling of nitrocellulose lacquers

**Addition:** 3 - 5% on total formulation

**Incorporation:** EFKA-3037 can be added either during or after the batch preparation.

**Storage:** EFKA-3037 should be stored in a cool dry place. When kept in an original

unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

**Packaging:** 25 kg and 170 kg non-returnable containers