

Levelling agent for solvent based and solvent-free coatings

Fluorocarbon-modified polymer Composition:

Data: Active ingredients : 69 - 71%

> Solvent xylene

: 0.97 - 0.99 g/cm³ Density at 20 °C DIN 51757 Flashpoint 25 °C ISO 3679 Colour ISO 4630 : max. 3

Appearance : clear, colourless liquid

Properties: EFKA-3777:

improves levelling

prevents cratering

helps substrate wetting

acts as a defoamer and de-aeration aid

does not interfere with intercoat adhesion

Application: EFKA-3777 is especially suitable for:

stoving enamels based on alkyd, acrylic and polyester resins

polyurethane coatings

2-pack epoxy compounds

air-dried alkyd systems

Addition: 0.5 - 2.0% on total formulation

EFKA-3777 should be added at the end of the batch preparation. Incorporation:

Storage: EFKA-3777 should be stored in a cool dry place. When kept in an original

unopened container, it will keep up to 5 years from the date of

manufacture. The expiry date is indicated on the container.

Packaging: 25 kg and 190 kg non-returnable containers