

Levelling agent for coil coatings and other solvent-based and solvent-free coatings

Composition: Acrylic copolymer

Data: Active ingredients : 69 - 71%

Solvent : alkyl benzene with high boiling point

(185 - 209 °C)

 Density at 20 °C
 : 0.98 - 1.00 g/cm³
 DIN 51757

 Flashpoint
 : 49 °C
 ISO 3679

 Colour
 : max. 3
 ISO 4630

Appearance : clear to slightly hazy, colourless liquid

Properties: EFKA-3778:

improves levellingprevents cratering

helps substrate wetting

· does not interfere with intercoat adhesion

Application: EFKA-3778 is especially suitable for:

coil coatings

polyurethane coatings

stoving enamels

2-pack epoxy compoundsair-dried alkyd systems

Addition: 0.5 - 2.0% on total formulation

Incorporation: EFKA-3778 should be added at the end of the batch preparation.

Storage: EFKA-3778 should be stored in a cool dry place. When kept in an original

unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging: 25 kg and 190 kg non-returnable containers